


TT403GR



Labels for Life.



Face Stock: 2.4 mil topcoated gloss green polyimide film offering excellent chemical resistance combined with superior high heat resistance. The material will not curl and is designed to survive high temperatures of lead-free solder processes.

Adhesive: Adhesive: 2.0 mil high performance permanent acrylic pressure sensitive adhesive offering exceptional resistance to harsh PCB cleaning solvents and high heat.

Release Liner: 55# glassine liner or a 1.5 mil polyester liner designed to offer excellent performance for both manual and automatic application

Thermal Transfer Green Polyimide Film

TT403GR is designed for thermal transfer printing of variable information for circuit board & component labeling. This high performance material withstands multiple passes through inline and batch cleaning processes; as well as very good resistance to most fluxes. TT403GR performs well through most lead and lead-free reflow processes. Green color signifies that the board complies with lead-free environmental requirements.

Typical Applications

In process circuit board & electronic component labeling.

Typical Industry Sectors

Medical
Electronics
Industrial










www.identco.com

TT403GR

Thermal Transfer Green Polyimide Film



Labels for Life.

	Agency Recognitions UL-MH16873/MH16225												
	Adhesion <table border="1"><thead><tr><th>Stainless Steel</th><th></th><th>Epoxy Panel</th><th></th></tr></thead><tbody><tr><td>20 minute dwell</td><td>35 oz/in (39 N/100mm)</td><td>20 minute dwell</td><td>35 oz/in (39 N/100mm)</td></tr><tr><td>24 hours</td><td>43 oz/in (47 N/100mm)</td><td>24 hour dwell</td><td>38 oz/in (42 N/100mm)</td></tr></tbody></table>	Stainless Steel		Epoxy Panel		20 minute dwell	35 oz/in (39 N/100mm)	20 minute dwell	35 oz/in (39 N/100mm)	24 hours	43 oz/in (47 N/100mm)	24 hour dwell	38 oz/in (42 N/100mm)
Stainless Steel		Epoxy Panel											
20 minute dwell	35 oz/in (39 N/100mm)	20 minute dwell	35 oz/in (39 N/100mm)										
24 hours	43 oz/in (47 N/100mm)	24 hour dwell	38 oz/in (42 N/100mm)										
	Material Caliper See following charts for specific details.												
	Exterior Durability Recommended: Indoor use only												
	Temperature Range See following charts for specific Temperature Ranges.												
	Shelf Life Recommended Storage: 45-90 ° F (7-32 ° C) 20-75% R.H. Shelf Life: 2 years @ recommended storage												
	Recommended Ribbons TTRR-B TTRR-D TTRR-CR												

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by IDENTCO customers for designs and specifications, or be relied on as meeting specific performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact IDENTCO for further information. Revised 11/1/2016

UNITED STATES HEADQUARTERS

28164 W. Concrete Drive
Ingleside, IL 60041
Phone: +1 (815) 385 - 0011
Fax +1 (815) 385 - 0359

MEXICO MONTERREY

Carr. a Laredo Km. 16.5 Interior
14B, Col. Moisés Sáenz, 66613
Apodaca, Nuevo Leon
Phone: +52 (81) 8008 - 0438

GERMANY FRANKFURT

Güterbahnhofstrasse 3-7
63450 Hanau
Phone: +49 (6181) 440 830 - 0
Fax: +49 (6181) 440 830 - 99

PRC HONG KONG

Unit 1708, 17/F, 9 Wing Hong St.
Cheung Sha Wan, Kowloon
Phone: +852 2959 2156
Fax: +852 2959 2019

MALAYSIA PENANG

Suite 163E, Level 16, Room 1602
Hunza Tower Gurney Paragon
Jalan Kelawei, Georgetown
10250 Penang
Phone: +6012 466 - 0866

TT403GR

Thermal Transfer Gloss Green Polyimide Film



Labels for Life.

Product Details

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Thickness	ASTM D 1000 Substrate (Topcoat & Film) Adhesive Liner (Glassine/Polyester) Total	0.0024" (0.0610 mm) 0.0002" (0.051 mm) 0.0031/0.0015" (0.079/0.038 mm) 0.0075/0.0059" (0.195/0.150 mm)
Adhesion to: Stainless Steel Exopy PC Board	ASTM D 1000 20 minute dwell 24 hours dwell 20 minute dwell 24 hours dwell	35 oz/in (39 N/100mm) 43 oz/in (47 N/100mm) 35 oz/in (39 N/100mm) 38 oz/in (42 N/100)
Tack	ASTM 2979 Polyken Probe Tack	11 oz (310 g)
Drop Shear	PSTC-7 (1/2" x 1" sample)	100 hours
Dielectric Strength	ASTM D1000	10,000 volts

Performance Properties

PHYSICAL PROPERTIES	TEST METHODS	AVERAGE RESULTS
Short Term High Service Temperature	80 seconds at 572F (300C)	No visible effect
	5 minutes at 500F (260C)	No visible effect
	2 hours at 338F (170C)	No visible effect
Long Term High Service Temperature	1000 hours at 212F (100C)	No visible effect
Low Service Temperature	1000 hours at -94F (-70C)"	No visible effect
Humidity Resistance	1000 hours at 98F (37C), 95% R.H.	No visible effect
UV Light Resistance"	30 days in UV Sunlighter 100	Topcoat turns yellow, label remains functional
Weatherability	1000 hours in Xenon Arc Weatherometer	Slight discoloration
Salt Fog Resistance	ASTM B 117 30 days in 5% salt fog solution chamber	No visible effect
Abrasion Resistance	Taber Abraser, CS-10 grinding wheels, 500 g/arm (Fed. Std. 191A, Method 5306	Print legible after 100 cycles
Chemical Vapor Phase Resistance	Labels adhered to epoxy PC board and exposed to the vapor of the boiling chemical for 10 minutes and then rubbed with a cotton swab saturated with the chemical for 10 rubs. Testing samples were baked 4 minutes at 160C prior to testing Ionox 3955 Micronox MX2501"	Severe print removal Complete print removal

Performance properties tested on TT403 printed with IDENTCO Series TTRR-D thermal transfer ribbon. Printed samples of TT403 were laminated to aluminum and allowed to dwell 24 hours before exposure to the indicated environmental conditions.

* TT403 is not recommended for outdoor use.

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by IDENTCO customers for designs and specifications, or be relied on as meeting specific performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact IDENTCO for further information. Revised 02/27/2017.

UNITED STATES HEADQUARTERS

28164 W. Concrete Drive
Ingleside, IL 60041
Phone: +1 (815) 385 - 0011
Fax +1 (815) 385 - 0359

MEXICO MONTERREY

Carr. a Laredo Km. 16.5 Interior
14B, Col. Moisés Sáenz, 66613
Apodaca, Nuevo Leon
Phone: +52 (81) 8008 - 0438

GERMANY FRANKFURT

Güterbahnhofstrasse 3-7
63450 Hanau
Phone: +49 (6181) 440 830 - 0
Fax: +49 (6181) 440 830 - 99

PRC HONG KONG

Unit 1708, 17/F, 9 Wing Hong St.
Cheung Sha Wan, Kowloon
Phone: +852 2959 2156
Fax: +852 2959 2019

MALAYSIA PENANG

Suite 163E, Level 16, Room 1602
Hunza Tower Gurney Paragon
Jalan Kelawai, Georgetown
10250 Penang
Phone: +6012 466 - 0866

TT403GR

Thermal Transfer Gloss Green Polyimide Film



Labels for Life.

Performance Properties

PERFORMANCE PROPERTIES		CHEMICAL RESISTANCE			
CHEMICAL REAGENT		SUBJECTIVE OBSERVATION OF VISIBLE CHANGE			
	EFFECT TO LABEL	RIBBON PERFORMANCE: TTRR-B, TTRR-CR, TTRR-D			
		WITHOUT RUB	WITH RUB		
			TTRR-B	TTRR-CR	TTRR-D
Kyzen Corp. 15% Aquanox® A4625 at 140F (60C)	No visible effect	1	5	5	2
Kyzen Corp. 17% Aquanox® A4520 at 140F (60C)	No visible effect	1	5	2	1
Kyzen Corp. 10% Aquanox® A4638 at 150F (65C)	No visible effect	1	1	1	1
Kyzen Corp. 20% Aquanox® A4703 at 145F (63C)	No visible effect	1	5	3	1
Zestron, 15% Atron® AC205 at 150F (65)	No visible effect	1	5	4	2
Zestron, 15% Atron® AC207 at 150F (65)	No visible effect	1	5	5	4
Zestron, 15% Vigon® A201 at 150F (65)	No visible effect	1	5	5	3
Zestron, 15% Vigon® N600 at 150F (65)	No visible effect	1	5	4	1
Isopropyl Alcohol 99% at 180F (82C)	No visible effect	1	1	1	1
Deionized Water AT 212F (100C)	No visible effect	1	1	1	1

Samples printed with TTRR-B, TTRR-CR, & TTRR-D thermal transfer ribbons. Samples laminated to epoxy PC board. Test samples exposed to indicated environments. Test samples baked 4 minutes at 160°C before testing. All test samples were immersed in the test fluids for 10 minutes. Samples were rubbed 10 times with cotton swab saturated with the test fluid.

Rating Scale: 1=no visible effect. 2=slight smear or print removal, detectable but minimal smear. 3=moderate smear or print removal (print still legible). 4=severe smear or print removal (print illegible or just barely legible). 5=complete print removal.

PERFORMANCE PROPERTIES		CHEMICAL RESISTANCE	
Solvent Resistance TEST FLUID		MIL-STD202G, Method 215K RESULTS TTRR-D	
Solvent A 1 part IPA, 3 parts mineral spirits		Meets Requirement	
Solvent B Terpene Defluxer		Meets Requirement	
Solvent C Saponifier @ 70C		Meets Requirement	

Test samples were printed with TTRR-D thermal transfer ribbon. Labels were printed with alphanumerics and barcodes. Test samples were subjected to 3 cycles of 3 minute immersions immediately followed by a toothbrush rub after each immersion.

Product testing, customer feedback and history of similar products support a customer performance expectation of at least two years from the date of receipt for this product as long as this product is stored in its original packaging in an environment between 45-90°F (7-32°C) and 20-75% RH. We are confident that our product will perform well beyond this time frame however it remains the responsibility of the user to assess the risk of using such product. We encourage customers to develop functional testing protocols that will qualify a product's fitness for use in their actual applications.

Trademarks: ANSI: American National Standards Institute (U.S.A.). ASTM: American Society for Testing and Materials (U.S.A.). All S.I. Units (metric) are mathematically derived from the U.S. Conventional Units. Aquanox® is a registered trademark of the Kyzen Corporation. Atron® is a registered trademark of Zestron Corporation. Ionox® is a registered trademark of the Kyzen Corporation. Micronox® is a registered trademark of the Kyzen Corporation. Polyken™ is a trademark of Testing Machines Inc. PSTC: Pressure Sensitive Tape Council (U.S.A.). UL: Underwriters Laboratories Inc. (U.S.A.). Vigon® is a registered trademark of Zestron Corporation. Weather-Ometer® is a registered trademark of Atlas material Testing Technology LLC.

Material may not be reproduced or distributed in any form with written permission.

Note: All values shown are averages and should not be used for specification purposes. Test data and test results contained in this document are for general information only and shall not be relied upon by IDENTCO customers for designs and specifications, or be relied on as meeting specific performance criteria. Customers desiring to develop specifications or performance criteria for specific product applications should contact IDENTCO for further information. Revised 02/27/2017.

UNITED STATES HEADQUARTERS

28164 W. Concrete Drive
Ingleside, IL 60041
Phone: +1 (815) 385 - 0011
Fax +1 (815) 385 - 0359

MEXICO MONTERREY

Carr. a Laredo Km. 16.5 Interior
14B, Col. Moisés Sáenz, 66613
Apodaca, Nuevo Leon
Phone: +52 (81) 8008 - 0438

GERMANY FRANKFURT

Güterbahnhofstrasse 3-7
63450 Hanau
Phone: +49 (6181) 440 830 - 0
Fax: +49 (6181) 440 830 - 99

PRC HONG KONG

Unit 1708, 17/F, 9 Wing Hong St.
Cheung Sha Wan, Kowloon
Phone: +852 2959 2156
Fax: +852 2959 2019

MALAYSIA PENANG

Suite 163E, Level 16, Room 1602
Hunza Tower Gurney Paragon
Jalan Kelawei, Georgetown
10250 Penang
Phone: +6012 466 - 0866